


VpCI® METALWORKING PRODUCTS



# BioCorr®



## PRODUCT DESCRIPTION

BioCorr® Rust Preventative is a waterbased, biobased, and biodegradable rust preventative that is intended for preservation of metals in storage and during transportation. BioCorr® Rust Preventative provides multi-metal protection and is an excellent environmentally sound alternative to petroleum derived products. This ready-to-use formulation can provide protection for up to two years of indoor storage; or during shipments when combined with VpCI® packaging materials. Unlike rust preventative oils this product leaves a dry film on the surface of the metal that is virtually undetectable. This feature helps to create a clean workplace and prevents material waste. BioCorr® Rust Preventative is biodegradable; eliminating expensive disposal costs associated with oils.

BioCorr® Rust Preventative has been awarded USDA BioPreferred<sup>SM</sup> designation ([www.preferred.gov](http://www.preferred.gov)).

When using for transmission applications be sure to use our BioCorr ATF version"

## FEATURES

- Provides excellent multi-metal corrosion protection
- Combines film-forming additives with Vapor phase Corrosion Inhibitors
- Environmentally friendly and biodegradable
- Replaces hazardous mineral oils and flammable solvents
- Contains no chlorinated compounds, chromates, or nitrites
- Ready-to-use product
- Contains biostatic material
- Formulated with renewable raw materials, contains 64% biobased content
- USDA certified Biobased product

## APPLICATION

BioCorr® is a ready-to-use product and can be applied by dipping or spraying.

BioCorr® SC is supplied as a viscous concentrate and must be diluted and thoroughly mixed prior to use.

## TYPICAL APPLICATIONS

- Biodegradable preservative for machines and equipment
- Temporary coating for storage and shipment
- Protection of pipes, flanges, gears
- Cast iron, sheets, and coils

## TYPICAL PROPERTIES

### BioCorr®

Appearance	Milky white liquid
pH	8.4-9.1 (neat)
Density	8.3-8.4 lb/gal (1.00-1.01 kg/l)

### BioCorr® SC

Appearance	Clear amber liquid
pH	8.5-9.3 (1% water)
Density	7.8-7.9 lb/gal (0.93-0.95 kg/l)
NVC	89-93%

# STANDARD TEST METHODS AND RESULTS

ASTM D-1748	Humidity Chamber Hours		
	<b>Carbon Steel</b>	<b>Copper</b>	<b>Aluminum</b>
	600	160-200	160-200
ASTM D-1735	Water Fog		
ASTM D 4627-86	(Cast Iron Chip Test) - Pass		
ASTM D-6866-11	Determination of Biobased Content		
NACE RP0487-2000	Selection of Rust Preventives		

## STORAGE AND PACKAGING

BioCorr® Rust Preventative is packaged in 5 gallon (19 liter) pails, 55 gallon (208 liter) drums, liquid totes, and bulk.

Also available as EcoAir® BioCorr® in 12 oz. (340 g) compressed air cans, 12 per carton.

The product should be stored sealed. Agitate before each use. The shelf life of BioCorr® Rust Preventative is up to 24 months.

BioCorr® SC is a viscous superconcentrate that should be diluted at 1:19 and thoroughly mixed prior to use.

BioCorr® Green is available with green tint to aid in visual inspection.

Note: Please see the Safety Data Sheet (SDS) for proper handling of the product.

**FOR INDUSTRIAL USE ONLY**  
**KEEP OUT OF REACH OF CHILDREN**  
**KEEP CONTAINER TIGHTLY CLOSED**  
**NOT FOR INTERNAL CONSUMPTION**  
**CONSULT SAFETY DATA SHEET FOR MORE INFORMATION**

### LIMITED WARRANTY

All statements, technical information and recommendations contained herein are based on tests Cortec® Corporation believes to be reliable, but the accuracy or completeness thereof is not guaranteed.

Cortec® Corporation warrants Cortec® products will be free from defects when shipped to customer. Cortec® Corporation's obligation under this warranty shall be limited to replacement of product that proves to be defective. To obtain replacement product under this warranty, the customer must notify Cortec® Corporation of the claimed defect within six months after shipment of product to customer. All freight charges for replacement products shall be paid by customer.

Cortec® Corporation shall have no liability for any injury, loss or damage arising out of the use of or the inability to use the products.  
BEFORE USING, USER SHALL DETERMINE THE SUITABILITY OF THE PRODUCT FOR ITS INTENDED USE,

AND USER ASSUMES ALL RISK AND LIABILITY WHATSOEVER IN CONNECTION THEREWITH. No representation or recommendation not contained herein shall have any force or effect unless in a written document signed by an officer of Cortec® Corporation.

THE FOREGOING WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES, EXPRESS, IMPLIED OR STATUTORY, INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO CASE SHALL CORTEC® CORPORATION BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES.



4119 White Bear Parkway, St. Paul, MN 55110 USA  
Phone (651) 429-1100, Fax (651) 429-1122  
Toll Free (800) 4-CORTEC, E-mail [info@cortecvci.com](mailto:info@cortecvci.com)  
<http://www.cortecvci.com>

Printed on recycled paper  100% post consumer

Revised: 10/15/18. Supersedes: 08/22/17. ©Cortec Corporation 2002-2018 of Cortec Corporation. All Rights Reserved. Copying of these materials in any form without the written authorization of Cortec Corporation is strictly prohibited. 2018, ©Cortec Corp. ISO accreditation applies to Cortec's processes only.

Distributed by:



**Valdamark Ltd**  
Unit 13,  
30 The Downs,  
Altrincham, Cheshire, WA14 2PX,  
United Kingdom.  
[info@valdamarkdirect.com](mailto:info@valdamarkdirect.com)  
Tel: +44 (0) 161 706 0388